

AMENDMENTS TO THE CLAIMS:

The following listing of claims replaces all prior listings, and all prior versions, of claims in the application.

LISTING OF CLAIMS:

1. (Currently amended) An adhesive sheet comprising:
_____ a polymer component, which includes acrylic rubber having a glass transition
temperature of -30° to 50°C, and a weight-average molecular weight of 50,000 to
1,000,000;
wherein the breaking strength of the adhesive sheet in a B-stage state is being
from 0.1 to 10 MPa at 25°C, and the breaking elongation thereof is being from 1 to 40%
at 25°C; and
_____ wherein the adhesive sheet has a property that it can be laminated together with
dicing tape onto a wafer prior to stealth dicing, and is capable of being subjected to
stealth dicing.

2. (Currently amended) The~~An~~ adhesive sheet according to claim 1,
~~comprising a polymer component,~~
wherein the elastic modulus of the adhesive sheet in a B-stage state is being from
1 to 3000 MPa in measurement of the dynamic viscoelasticity at 25°C and 10 Hz, and
the elastic modulus thereof being from 4000 to 20000 MPa in measurement of the
dynamic viscoelasticity at 25°C and 900 Hz.

3. (Currently amended) ~~The~~An adhesive sheet according to claim 1,
~~comprising a polymer component,~~
wherein the elastic modulus of the adhesive sheet in a B-stage state ~~is~~being from
1 to 3000 MPa in measurement of the dynamic viscoelasticity at 25°C and 10 Hz, and
the elastic modulus thereof being from 4000 to 20000 MPa in measurement of the
dynamic viscoelasticity at -20°C and 10 Hz.

4. (Currently amended) The adhesive sheet according to claim 12,
~~comprising the polymer component, and~~
wherein the elastic modulus of the adhesive sheet in a B-stage state ~~is~~being from
0.1 to 20 MPa in measurement of the dynamic viscoelasticity at 60°C and 10 Hz.

5. and 6. (Cancelled).

7. (Currently amended) The adhesive sheet according to claim 16, wherein
the acrylic rubber~~the polymer component, which has a glass transition temperature of~~
~~30 to 50°C and a weight average molecular weight of 50000 to 1000000,~~ is contained in
an amount of 50% or less of the total weight of the adhesive sheet ~~from which the~~
~~weight of a filler is removed.~~

8. and 9. (Cancelled).

10. (Previously presented) The adhesive sheet according to claim 1, wherein the content of remaining volatile matters is from 0.01 to 3% by weight.

11. (Previously presented) The adhesive sheet according to claim 1, which has a film thickness of 1 to 250 μm .

12. – 43. (Cancelled).

44. – 49. (Not entered).

50. (New) The adhesive sheet according to claim 1, wherein the acrylic rubber is contained in an amount of 35% or less of the total weight of the adhesive sheet.

51. (New) The adhesive sheet according to claim 46, wherein the acrylic rubber is contained in an amount of from 25% to 35% of the total weight of the adhesive sheet.

52. (New) The adhesive sheet according to claim 1, wherein the polymer component further includes epoxy resin.

53. (New) The adhesive sheet according to claim 1, laminated together with the dicing tape onto the wafer, prior to the stealth dicing.